




## TECHNICAL DATA SHEET

# ZERO VOC

Single-two component waterborne finishing treatment for wood floors



1 Gal. - 9,0 fl.oz. BOOST



### DESCRIPTION

Polyurethane waterborne finishing treatment completely solvent-free. ZERO VOC can be used both as a single component or, after the addition of ZERO VOC BOOST as a two-component treatment. Produced with renewable raw materials, ZERO VOC is ideal for use in green building and when applied directly, it leaves the shade of wood unaltered and provides a very natural effect. The treatment cycle consists in the application of a first coat of product as it is, directly on the wood. After at last 3 hours, (the product dries completely according to environmental conditions) and after a light sanding (from 180 grain upwards), apply the second coat of single component or two component if catalyzed with about 7% of the special ZERO VOC BOOST (which is also free of VOCs and hazard labels). Apart from the absence of solvents, the other considerable advantage of ZERO VOC is that if any leftover product mixed with its specific CROSSLINKER is placed in a separate perfectly sealed container, it has a POT-LIFE of up to 7 days. This enables the product to be re-used within a few days from mixing without leaving any residue to be disposed of, in full respect of the environment. Once this time limit has been exceeded, the increased performance due to the CROSSLINKER will gradually decrease over time and the catalysis can be repeated if a high performance is required. Excess ZERO VOC BOOST (over 7%) will delay the complete drying of the finish quite considerably.

TECHNICAL DATA CHEMICAL-PHYSICAL CHARACTERISTICS at 65°F (indicative values not constituting product specifications):	
Dust dry (minutes)	20
Impression dry (minutes)	35
Dry for sanding (hours)	3/5
Overcoating without sanding	Not recommended
Light Traffic (hours)	8/16
Careful Use (days)	2/3
Completely Dry (days)	10
Dry for sanding with Crosslinker - 506382 ZERO VOC BOOST (hours)	12/16
Light Traffic with Crosslinker - 506382 ZERO VOC BOOST (hours)	24/36
Careful Use with Crosslinker - 506382 ZERO VOC BOOST (days)	3/5
Completely Dry with Crosslinker - 506382 ZERO VOC BOOST (days)	10
Degree of gloss - ZERO VOC X-MATT (gloss)	15
Degree of gloss - ZERO VOC SATIN (gloss)	30
Degree of gloss - ZERO VOC SEMIGLOSS (gloss)	60
Taber Test (1000 revs., 1000 g, abrasive wheel CS10) (mg)	35
Taber Test (1000 revs., 1000 g, abrasive wheel CS10) with Crosslinker - 506382 ZERO VOC BOOST (mg)	25
Application method	Roller 3/8", brush,T-bar, pad
Average coverage per coat (sq.ft./Gal.)	350/500
Adhesion (checkering) (%)	100
Stability and storage (in original, unopened containers stored in a cool, dry place) (months)	12
US Regulatory VOC Compliant (g/lt)	<5
US Regulatory VOC Compliant with Crosslinker (g/lt)	<5
Max permitted dilution	Water max 5%
To clean tools	Water
Standard packaging (Gal.)	4x1
Standard packaging ZERO VOC BOOST (fl. oz.)	1x9,0 (q.ty for 1 Gal. of ZERO VOC)

### APPLICATION

Sand and prepare floor using NOFMA-NWFA accepted methods. It is very important to apply a first, even and abundant coat of ZERO VOC (about 350/500 sf./Gal.) with a roller or a brush. On rough wood, a smaller quantity than that recommended should be applied when the temperature is high and/or the humidity is low; with the natural absorption of the finish by the wood, greater coverage may be visible in correspondence with the lapmarks. According to environmental conditions, after about 3 hours, sand with a fine grain (180/220) and remove all the residue dust. Apply the finishing coat in the same way as described previously. For those places subject to heavy traffic (shops, offices, living rooms) we recommend use of the cross-linking agent ZERO VOC BOOST in quantities of 7% also in the first coat as it greatly improves resistance to abrasion and to staining.





## MAINTENANCE

The maintenance of floors treated with ZERO VOC must only be carried out using DETERGENTE NEUTRO and/or IDRONET. Do not use alcohol, ammonia or detergents for hard surfaces.  
For further information see the MAINTENANCE SHEET.

## SPECIAL RECOMMENDATIONS

If the product is used on exotic and/or little known woods it is always advisable to carry out preliminary tests as in some cases (e.g. on IPE LAPACHO) the application of waterborne finishes directly on the wood or on primers that are not perfectly insulating may cause a considerable reddening of the film.

Always prepare a test area to verify the compatibility of the products used and verify that the final outcome is the desired.

Vermeister always recommends the use of two-component sealers or finishes on stains. Allow stains to dry according to the manufacturer's recommendations.

## NOTES

A "fresh on fresh" application is not recommended. The addition of ZERO VOC BOOST prolongs the drying time of the finish: FOLLOW THE RATIOS FOR USE (MAX 7%). The application of the product on solvent based primers and finishes could cause separation. The floor is ready for traffic after 36/48 hours. Do not apply the product under 50°F or over 85°F.

Stir well before use – Store above freezing.

DRY FOR SANDING: interval before the floor is ready for sanding

LIGHT TRAFFIC: interval before several people can walk on the floor.

CAREFUL USE: interval before the floor is ready for moderate use.

COMPLETELY DRY: interval before the floor is ready for complete use: e.g. for furniture removal, to allow other craftsmen to carry out work, to start maintenance of the floor, etc.

Safety precautions. Keep the product in a tightly closed, upright container in a cool place away from sources of heat. The information for the user is given in the relevant safety sheet. Empty containers or those containing slight traces of the product must be disposed of in accordance with local regulations. Vermeister America, Inc. guarantees that the details given in this sheet are provided to the best of the company's technical-scientific knowledge and experience; however, the company cannot be held responsible in any way for the results obtained with the products as the conditions of application are beyond the company's control. It is always advisable to check the suitability of the product to each specific circumstance. This sheet cancels and replaces all previous editions.  
FOR TECHNICAL ADVICE call Vermeister America, Inc. at (800) 532- 1308.